

Durethan BC 30 S 000000

PA 6, non-reinforced, injection moulding,
 ISO Shortname: ISO 1874-PA 6 ,GR,14-030

Property	Test Condition	Unit	Standard	guide value	cond.
				d.a.m.	
Rheological properties					
C Molding shrinkage, parallel	60x60x2; 270 °C / WZ 80 °C; 600 bar	%	ISO 294-4	1.03	
C Molding shrinkage, transverse	60x60x2; 270 °C / WZ 80 °C; 600 bar	%	ISO 294-4	0.91	
Post- shrinkage, parallel	60x60x2; 120 °C; 4 h	%	ISO 294-4	0.27	
Post- shrinkage, transverse	60x60x2; 120 °C; 4 h	%	ISO 294-4	0.27	
Mechanical properties (23 °C/50 % r. h.)					
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	3200	
C Yield stress	50 mm/min	MPa	ISO 527-1,-2	80	
C Charpy impact strength	23 °C	kJ/m ²	ISO 179-1eU	N	
C Charpy notched impact strength	23 °C	kJ/m ²	ISO 179-1eA	<10	
C Charpy notched impact strength	-30 °C	kJ/m ²	ISO 179-1eA	<10	
Izod impact strength	23 °C	kJ/m ²	ISO 180-1U	N	
Izod impact strength	-30 °C	kJ/m ²	ISO 180-1U	200	
Izod notched impact strength	23 °C	kJ/m ²	ISO 180-1A	<10	
Izod notched impact strength	-30 °C	kJ/m ²	ISO 180-1A	<10	
Flexural modulus	2 mm/min	MPa	ISO 178-A	2800	
Flexural strength	2 mm/min	MPa	ISO 178-A	105	
Flexural strain at flexural strength	2 mm/min	%	ISO 178-A	6.0	
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178-A	90	
Thermal properties					
C Melting temperature	10 °C/min	°C	ISO 11357-1,-3	221	
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	66	
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	172	
Other properties (23 °C)					
C Density		kg/m ³	ISO 1183	1122	
Processing conditions for test specimens					
C Injection molding-Melt temperature		°C	ISO 294	270	
C Injection molding-Mold temperature		°C	ISO 294	80	
Processing recommendations					
Drying temperature dry air dryer		°C	-	80	
Drying time dry air dryer		h	-	2-6	
Residual moisture content		%	Acc. to Karl Fischer	0.03-0.12	
Melt temperature (Tmin - Tmax)		°C	-	260-280	
Mold temperature		°C	-	80-90	



Durethan BC 30 S 000000

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.



Durethan BC 30 S 000000

Disclaimer

Disclaimer for developmental products

This is a Sales Product at the developmental stage (a Trial Product). For this reason, no assurances can be given as to type conformity, processability, long-term performance characteristics or other production or application parameters. No definitive statements can be made regarding the behavior of the product during processing or use. The purchaser/user uses the product entirely at his own risk. The marketing and continued supply of this material are not assured and may be discontinued at any time. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Test values

Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the coloring.

Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

Conditioning

Conditioning in accordance with ISO 1110 (70 °C; 62 % r.h.)

LANXESS DEUTSCHLAND GMBH | D - 51369 LEVERKUSEN

© LANXESS Deutschland GmbH

